


tutorial session VI

domains



domain

(3D) extended modification of the crystal structure

locally changed structure domains in a strict sense
some nm to some μm

local dissolutions cluster

aspects needed to describe a domain


orientation relationship host \Leftrightarrow guest (ir)regular intergrowth
lattice_{host} \Leftrightarrow lattice_{guest}

interface host \Leftrightarrow guest smooth interface
rough, irregular interface


distribution of domains (irr)regular distribution

origin

very often in connection with phase transitions
indirectly in relation to host/guest structures and intercalated structures




Introductory examples




simple domain
identical lattice
smooth interface

if randomly distributed:
diffuse maxima at
common Bragg reflections




simple domain
different structure
smooth interface

if randomly distributed:
diffuse maxima at
individual Bragg reflections



simple domain
different structure
uneven interface

diffuse maxima at
individual Bragg reflections



Exercise 1




Run `discus_suite`

Switch to directory:

`Lectures/10_Domain/CUBE`

Use Macro `dom.cube.mac`

`suite > @dom.cube.mac`



Use


jmol with file `cube.cif`

As well

```

read                                     # switch to read menu
cell dom.host.cube.cell,7,7,1          # read an asymmetric unit expand
#
domain                                  # switch to domain level
  rese                                  # reset everything
  mode  pseudo                          # Interpret pseudo atoms
  input  dom.cube.pseudo                # List of domain origins
  assign char,si,cube                   # interpret "SI" as a cube shaped
  assign fuzzy,si,1.5                   # define distance to host atoms
  assign cont, si,dom.guest.cube.stru   # domain structure is in this file
  assign shape ,si,1,  1. , 0. , 0. , 0. # Define a cube shaped domain
  assign shape ,si,2,  0. , 1. , 0. , 0. # that is +- 1 unit cells large
  assign shape ,si,3,  0. , 0. , 1. , 0. #
  assign orient,si,1,  1. , 0. , 0. , 0. # Domain content shall be rotated
  assign orient,si,2,  0. , 1. , 0. , 0. # by this matrix (here unit matrix)
  assign orient,si,3,  0. , 0. , 1. , 0. #
  set      distance, all, 2.55           # Define distance to internal
  set      distance, new, 2.71          # boundary for old and new atoms
  show
  run
exit


```



```
title Domain list for simple domains
spcgr  P4
cell   2.50, 2.50, 2.50, 90.00, 90.00, 90.00
atom
SI      0.00000  0.00000  0.00000  0.05
```

The domain list is a simple DISCUS structure file

Here one pseudo atom at 0,0,0





Run discus_suite

Switch to directory:

Lectures/10_Domain/CUBE


Use Macro dom.cube.mac

suite > @dom.cube.mac

Edit file dom.cube.pseudo

Change the position of the Si atom,


Add new Si atoms...



Use

jmol with file cube.cif

as well




Run `discus_suite`

Switch to directory:
Lectures/10_Domain/CUBE

Use Macro `dom.tilt.mac`

`suite > @dom.tilt.mac`


Edit file `dom.tilt.mac`
Lines 46 to 48 contain a rotation matrix




Use

`jmol` with file `tilt.cif`

as well



Example: Perovskite



high temperature phase

cubic $Pm\bar{3}m$

Ti $0,0,0$ **octahedron site**

Sr $\frac{1}{2}, \frac{1}{2}, \frac{1}{2}$

O $\frac{1}{2}, 0, 0$

low temperature phase (simplified)

tetragonal $P4mm$

$c/a \neq 1$

shift of Ti along $[001]$

in $Pm\bar{3}m$ equivalent:

independent nucleation

relaxation within one unit cell

$[100]$

$[010]$

$[001]$

three different possible orientations

equal relaxation in neighboring cells



simulation of the disordered low temperature structure

A) random selection of individual unit cells ==> introduce a local distortion

relax neighboring cells (in random sequence)
until whole crystal has been distorted


extended book keeping and search for unit cells that are distorted already!

B) 'detour' via dummy-atoms (dummy-domains)

1. cubic primitive crystal with three different atoms A,B,C at equal amounts
2. sort atoms A,B,C with positive correlation
3. relax distances A-A, B-B, C-C
4. replace atoms A by unit cell distorted along [100]
replace atoms B by unit cell distorted along [010]
replace atoms C by unit cell distorted along [001]

B) 'detour' via dummy-atoms (dummy-domains)

1. cubic primitive crystal with three atoms A,B,C in equal amounts



atom A represents a unit cell
that is distorted along [100]
correspondingly for B and C

Distance between atoms:
atom position:


lattice constant a
 $0,0,0$

2. sort atoms A,B,C with positive correlations

Neighbors along: $\langle 100 \rangle$

pairs: A-B, A-C, B-C
each with correlation > 0

Crystal, build up of three different 'atoms',
all at ideal positions, no distortions




Example: Perovskite



B) 'detour' via dummy atoms (dummy domains)

3. local distortions



pair A-A:distance along

$[100]$ is $a_0 \cdot k$
 $[010]$ is a_0/k
 $[001]$ is a_0/k

with $k \sim 1.0025$

pair A-X:distance along


$[100]$ is a_0
 $[010]$ is a_0
 $[001]$ is a_0


distortion of A along $[100]$ induces
 shift of $/C$ along $[100]$

angle A-A-A

90°

If interface is long,
 dislocations will occur







Example: Perovskite



diffraction pattern of the relaxed structure

all 'atoms' are identical!




diffuse maxima at Bragg positions

extended domains of locally equal atoms

weak diffuse streaks


shift of the domains





B) 'detour' via dummy atoms (dummy domains)

4. replace atoms A by a unit cell that is distorted along [100]
correspondingly replace B by a unit cell that is distorted along [010]
correspondingly for C



metric remains cubic

transform atoms within a [100] domain by:

$$\begin{pmatrix} k & 0 & 0 \\ 0 & 1/k & 0 \\ 0 & 0 & 1/k \end{pmatrix} \begin{pmatrix} x \\ y \\ z \end{pmatrix}$$



in addition, relative shift of atoms along $\pm[100]$



Example: Perovskite



diffraction pattern of the relaxed and replaced structure



diffuse maxima at Bragg positions

extended domains that consist of unit cells, locally distorted along the same direction

$$I_{h+k+l} = 2n > I_{h+k+l} = 2n+1$$

weak diffuse streaks

shift of domains





Run discus_suite

Switch to directory:

Lectures/10_Domain/Perovskite

Use Macro dom.perov.mac

suite > @dom.perov.mac

The macro takes you through the steps

Plots follow at the end

